

DEGACOTE C2

SECTION 2

TOP COAT



PRODUCT INFORMATION BULLETIN

JANUARY 2007

Page 1 of 2

DESCRIPTION

Degacote C2 is a tough, elastic, waterproof, methacrylate resin cured by the addition of a controlled amount of Degacote hardener powder.

USE

1. As a coating for coloured pavements on primed concrete or cleaned bitumen substrates.
2. As a base coat for high duty skid resistant coatings. (Aggregate size to 1mm.)
3. As a pigmented top coat for Degacote C1 / C3 skid resistant coatings, it encapsulates the aggregate to ensure skid resistance is maintained for the coatings designed life.

APPLICATION

Brush or roller.

CLEAN UP

Degacote cleaning solvent or general all purpose thinners.

APPLICATION RATE

Depends on substrate and grade of aggregate used.

0.2 Ltr/sq metre for 0.5 mm aggregate.

1.0 – 1.5 Ltr/sq metre for 4 – 6mm aggregate.

CURING TIME

30 minutes at 20°C.

DURABILITY

Depends on service conditions and applied thickness. When correctly applied to manufacturer's instructions a life expectancy of up to 10 years can be achieved.

DEGACOTE C2
SECTION 2
TOP COAT (continued)



PRODUCT INFORMATION BULLETIN

JANUARY 2007

Page 2 of 2

COLOUR RANGE

White, Yellow, Black, Terracotta, Brazen Red, Dove Grey, Seagull Grey.

SPECIAL NOTES

1. Due to the high wear resistance of Degacote C2 slight tyre marks may appear during the long life of the product.
2. In the event of mechanical damage Degacote C2 coatings are easily repaired using the same product.

HARDENER POWDER ADDITION, POT LIFE & CURING TIMES AT VARIOUS TEMPERATURES

Substrate Temp °C	Hardener Powder Addition Mills/Litre	Approximate Pot Life In Minutes	Approximate Curing Time In Minutes
+10°C	50	18	40
+15°C	35	12	25
+20°C	25	10	20
+25°C	20	10	20
+30°C	15	10	20

For any further details contact us on 03 9725 9590.

TERMS AND CONDITIONS OF SALE

All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy of completeness thereof is not guaranteed, and the following is made in lieu of all warranties, express or implied.

Sellers and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Neither seller nor manufacturer shall be liable for injury, loss or damage, direct or indirect or consequential, arising out of the use of or the inability to use the product. Before using, user shall determine the suitability of the product for his intended use, and user assumes all risk and liability whatsoever in connection therewith.

Statements or recommendations not contained herein shall have no force or effect unless in an agreement signed by officers of seller and manufacturer.

MELBOURNE
1 Shelley Court
Kilsyth Vic 3137
Ph (03) 9725 9590

BRISBANE
1/18 Boron Street
Sumner Park Qld 4074
Ph (07) 3376 6700

SYDNEY
P.O. BOX 499
Swansea NSW 2281
Ph 0403 266 780