

# DEGACOTE C3

## SECTION 2

### BASE COAT



---

#### PRODUCT INFORMATION BULLETIN

September 2011

Page 1 of 2

### DESCRIPTION

Degacote C3 is a tough, elastic, waterproof, methacrylate resin compound specially formulated for application to bitumen and primed concrete surfaces. Degacote C3 base coat is cured by the addition of a controlled amount of Degacote hardener powder.

### USE

As a base coat, either unpigmented or pigmented it provides a tough, waterproof, flexible aggregate holding coat for heavy duty skid resistant surfaces on concrete and bitumen roadways, bridge decks, ramps and factory floors.

### APPLICATION

By roller, squeegee or trowel depending on application thickness.

### CLEAN UP

Degacote cleaning solvent or general purpose thinners.

### APPLICATION RATE

Depends on the coating and grade of aggregate used.

1.0 Litre/sq metre for 2-3mm aggregate.

2.0 Litre/sq metre for 3-7mm aggregate.

### CURING TIME

30 minutes at 20°C.

### DURABILITY

Depends on service conditions and applied thickness. When correctly applied to manufacturer's instructions a 10 year life can be achieved.

# DEGACOTE C3

## SECTION 2

### BASE COAT (continued)



#### PRODUCT INFORMATION BULLETIN

September 2011

Page 2 of 2

### COLOUR RANGE

Standard colour supplied: Unpigmented.

Other colours available on order - White, Yellow, Black, Terracotta, Brazen Red, Dove Grey, Seagull Grey.

### SPECIAL NOTES

1. Degacote C3 base coatings are always sprinkled with aggregate and top coated with Degacote C2 top coat. The aggregate size depends on the surface end use and varies from 2mm for factory floors to 7mm for road and bridges.
2. In the event of mechanical damage Degacote C3 coatings are easily repaired using the same product.

### HARDENER POWDER ADDITION, POT LIFE & CURING TIMES AT VARIOUS TEMPERATURES

Substrate Temp °C	Hardener Powder Addition Mills/Litre	Approximate Pot Life In Minutes	Approximate Curing Time In Minutes
+10°C	35	30	70
+15°C	30	15	35
+20°C	25	10	25
+25°C	20	10	25
+30°C	15	10	25

For any further details contact us on 03 9725 9590.

#### TERMS AND CONDITIONS OF SALE

All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy of completeness thereof is not guaranteed, and the following is made in lieu of all warranties, express or implied.

Sellers and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Neither seller nor manufacturer shall be liable for injury, loss or damage, direct or indirect or consequential, arising out of the use of or the inability to use the product. Before using, user shall determine the suitability of the product for his intended use, and user assumes all risk and liability whatsoever in connection therewith.

Statements or recommendations not contained herein shall have no force or effect unless in an agreement signed by officers of seller and manufacturer.

**MELBOURNE**  
1 Shelley Court  
Kilsyth Vic 3137  
Ph (03) 9725 9590

**SYDNEY**  
1300 872 799

**BRISBANE**  
1/18 Boron Street  
Sumner Park Qld 4074  
Ph (07) 3376 6700