

DEGACOTE J1

SECTION 2

FLEXIBLE JOINTING COMPOUND



PRODUCT INFORMATION BULLETIN

JANUARY 2007

Page 1 of 2

DESCRIPTION

Degacote J1 Flexible Jointing Compound is an elastic, waterproof Methacrylate resin compound specially formulated for application to primed concrete surfaces. Degacote J1 Flexible Jointing Compound is cured by the addition of a controlled amount of Degacote Hardener Powder.

USE

As a flexible, self levelling, waterproof sealing compound for jointing concrete floor slabs. Degacote J1 is suitable for joint movement of up to 10% horizontal and 2.5% vertical. It is best applied when slab temperature is at a minimum, i.e. joint width at a maximum, so that the tensile stress on the concrete face is kept to a minimum.

APPLICATION

The product is mixed with the recommended amount of curing agent and poured into the prepared joint. Joints are usually made 15mm deep but in areas where high lift fork trucks with small fibre or steel wheels are operating the depth is increased to a minimum of 25mm.

Deep joints are filled as follows:

1. Fill joint to within 12mm of floor and when compound is cured,
2. Fill joint to floor level.

Note: If a flat surface is required overfill joint by 1mm and after curing grind flush.

APPLICATION RATE

Depends on the joint width and depth.
A 10mm wide x 15mm deep joint requires 0.15 Litre/Lineal Metre.

CURING TIME

30 minutes at 20°C.

DURABILITY

When correctly applied to manufacturer's instructions a 5 year minimum life can be expected.

Note: Refers to the product only and not the installation.

COLOUR RANGE

Dove Grey. Other colours by request.

CLEAN UP

Degacote Cleaning Solvent or general purpose thinners.

MELBOURNE
1 Shelley Court
Kilsyth Vic 3137
Ph (03) 9725 9590

BRISBANE
1/18 Boron Street
Sumner Park Qld 4074
Ph (07) 3376 6700

SYDNEY
P.O. BOX 499
Swansea NSW 2281
Ph 0403 266 780

DEGACOTE J1
SECTION 2
FLEXIBLE JOINTING COMPOUND (continued)
PRODUCT INFORMATION BULLETIN



JANUARY 2007

Page 2 of 2

**HARDENER POWDER ADDITION, POT LIFE & CURING TIMES AT
VARIOUS TEMPERATURES**

Substrate Temp °C	Hardener Powder Addition Mills/Litre	Approximate Pot Life In Minutes	Approximate Curing Time In Minutes
+10°C	60	15	25
+15°C	45	12	20
+20°C	30	10	20
+25°C	20	10	15
+30°C	15	7	15

For any further details contact us on 03 9725 9590.

TERMS AND CONDITIONS OF SALE

All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy of completeness thereof is not guaranteed, and the following is made in lieu of all warranties, express or implied.

Sellers and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Neither seller nor manufacturer shall be liable for injury, loss or damage, direct or indirect or consequential, arising out of the use of or the inability to use the product. Before using, user shall determine the suitability of the product for his intended use, and user assumes all risk and liability whatsoever in connection therewith.

Statements or recommendations not contained herein shall have no force or effect unless in an agreement signed by officers of seller and manufacturer.

MELBOURNE
1 Shelley Court
Kilsyth Vic 3137
Ph (03) 9725 9590

BRISBANE
1/18 Boron Street
Sumner Park Qld 4074
Ph (07) 3376 6700

SYDNEY
P.O. BOX 499
Swansea NSW 2281
Ph 0403 266 780