

DEGACOTE J2
SECTION 2
FLEXIBLE JOINTING COMPOUND
PRODUCT INFORMATION BULLETIN



Revised September 2011

Page 1 of 2

DESCRIPTION

Degacote J2 Jointing Compound is a highly viscous, extremely elastic, waterproof Methacrylate compound which hardens rapidly after the addition of Degacote Hardener Powder.

USE

1. Jointing of concrete slabs subjected to large movements.
2. Sealing of active cracks.

APPLICATION

The product is mixed with the recommended amount of curing agent and poured into the prepared joint or crack.

APPLICATION RATE

Depends on size of joint or crack.

CURING TIME

Approximately 25 minutes at 20⁰C.

DURABILITY

When correctly applied to the manufacturer's instructions a 5 year minimum life can be expected.

Note: Refers to the product only and not the installation.

COLOUR RANGE

Dove Grey. Other colours by request.

CLEAN UP

Degacote Cleaning Solvent or general purpose thinners.

DEGACOTE J2

SECTION 2

FLEXIBLE JOINTING COMPOUND (continued)



PRODUCT INFORMATION BULLETIN

Revised September 2011

Page 2 of 2

HARDENER POWDER ADDITION, POT LIFE & CURING TIMES AT VARIOUS TEMPERATURES

Substrate Temp °C	Hardener Powder Addition Mills/Litre	Approximate Pot Life In Minutes	Approximate Curing Time In Minutes
+10°C	70	25	70
+15°C	60	15	35
+20°C	50	10	25
+25°C	40	10	25
+30°C	30	10	25

For any further details contact us on 03 9725 9590.

Special Note:

1. Joint edges and cracks should be primed with Degadeck Crack Sealer to ensure the full potential of this product is achieved.
2. The product can be thickened for use on vertical joints and out of level surfaces by the addition of a few drops of Degacote thickening agent. Refer to your Degacote representative.
3. Jointing is best carried out when the concrete slabs are at or close to their minimum operating temperature, i.e. when the joint is at its widest. Temperature increases above this minimum will put the joint under compression and virtually eliminate the chance of cracking along the bond line with the concrete.

TERMS AND CONDITIONS OF SALE

All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy of completeness thereof is not guaranteed, and the following is made in lieu of all warranties, express or implied.

Sellers and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Neither seller nor manufacturer shall be liable for injury, loss or damage, direct or indirect or consequential, arising out of the use of or the inability to use the product. Before using, user shall determine the suitability of the product for his intended use, and user assumes all risk and liability whatsoever in connection therewith.

Statements or recommendations not contained herein shall have no force or effect unless in an agreement signed by officers of seller and manufacturer.

MELBOURNE
1 Shelley Court
Kilsyth Vic 3137
Ph (03) 9725 9590

SYDNEY
1300 872 799

BRISBANE
1/18 Boron Street
Summer Park Qld 4074
Ph (07) 3376 6700