

DEGACOTE P2

SECTION 2

PRIMER / SEALER



PRODUCT INFORMATION BULLETIN

January 2007

Page 1 of 2

DESCRIPTION

Degacote P2 Quick Cure Concrete Primer/Sealer is an environmentally friendly reactive methacrylate resin which hardens rapidly after the addition of Degacote Hardener Powder. When cured it provides a hard, abrasion resistant surface, resistant to a wide range of chemical spills.

USE

1. As a penetrating primer for the application of further TCP or Degacote coatings.
2. As a pigmented sealing coating it provides a hard wearing, U.V. stable, decorative finish for structural concrete and concrete floors. Glass beads can be used to increase skid resistance.

CHARACTERISTIC DATA *(Refer also Material Safety Data Sheets.)*

Form Supplied:		Liquid
Viscosity Range at 23⁰C		50 - 280 mpa
Density at 20⁰C	DIN 51757	1.01 gm / cm³
Flash Point	DIN 51755	+10⁰C
Shelf Life, Dark < 20⁰C		Min 6 months

APPLICATION

By brush, roller or squeegee to a dry, clean, prepared concrete surface.

THINNING & CLEAN UP

Degacote Cleaning Solvent or general purpose thinners. All tools should be cleaned before product fully hardens.

APPLICATION RATE

0.2 - 0.4 litres/sq metre depending on the absorbency of the concrete surface.

COLOUR RANGE

Clear (cures with a yellowish tinge), White, Yellow, Black, Terracotta, Brazen Red, Dove Grey, Seagull Grey.

DEGACOTE P2
SECTION 2
PRIMER / SEALER (continued)



PRODUCT INFORMATION BULLETIN

JANUARY 2007

Page 2 of 2

**HARDENER POWDER ADDITION, POT LIFE & CURING TIMES
AT VARIOUS TEMPERATURES**

SUBSTRATE TEMP °C	HARDENER POWDER ADDITION MLS/LTR	APPROXIMATE POT LIFE IN MINUTES	APPROXIMATE CURING TIME IN MINUTES
+10 ⁰ C	90	15	25
+15 ⁰ C	75	10	20
+20 ⁰ C	54	10	20
+25 ⁰ C	45	10	20
+30 ⁰ C	36	10	20

SPECIAL NOTE

When used as a concrete primer, if floor is to be left longer than 8 hours before further coating, it can be lightly sand dusted with 0.3 - 0.5mm sand for additional mechanical key.

For any further details contact us on 03 9725 9590.

TERMS AND CONDITIONS OF SALE

All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy of completeness thereof is not guaranteed, and the following is made in lieu of all warranties, express or implied.

Sellers and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Neither seller nor manufacturer shall be liable for injury, loss or damage, direct or indirect or consequential, arising out of the use of or the inability to use the product. Before using, user shall determine the suitability of the product for his intended use, and user assumes all risk and liability whatsoever in connection therewith.

Statements or recommendations not contained herein shall have no force or effect unless in an agreement signed by officers of seller and manufacturer.

MELBOURNE
1 Shelley Court
Kilsyth Vic 3137
Ph (03) 9725 9590

BRISBANE
1/18 Boron Street
Sumner Park Qld 4074
Ph (07) 3376 6700

SYDNEY
P.O. BOX 499
Swansea NSW 2281
Ph 0403 266 780